

C. L. Hauthaway & Sons Corporation  
638 Summer Street Lynn, MA 01905-2092

781 592-6444  
www.hauthaway.com

## Hauthane L-2896

**DESCRIPTION:** A polycarbonate-based, aliphatic, water-borne polyurethane dispersion.

**SUGGESTED USES:** **L-2896** was developed for general coatings use on wood, plastic and metal substrates. The product offers exceptional resistance to hydrolysis, oxidation and UV-degradation. L-2896 is ideally suited for exterior applications where film durability and longevity are important considerations.

**CHARACTERISTICS:**

- < Excellent exterior weathering durability
- < Excellent humidity resistance
- < Contains dipropylene glycol dimethyl ether (DMM) co-solvent

**APPLICATION:** **L-2896** may be formulated into coatings applied by spray, brush or pad applicator. It can be used as a sole vehicle or blended with acrylic emulsions. The rheology may be modified with associative thickeners.

**CURING:** Typical oven drying temperatures and dwell times for aqueous coatings are sufficient to produce optimal film properties. Enhanced film properties can be obtained when this product is crosslinked with any of a variety of external crosslinking agents.

### PHYSICAL PROPERTIES

<b>SOLIDS</b>	35% ( $\pm$ 1%)
<b>VISCOSITY</b>	50-500 cps
<b>DENSITY</b>	1.06
<b>pH</b>	7.5 - 10.0
<b>VOC CONTENT</b>	126 g/l (as supplied)
<b>SOFTENING POINT</b>	355°F

### TENSILE PROPERTIES

(TESTED AT 20 INCHES/MINUTE)	
<b>ELONGATION</b>	210 %
<b>TENSILE STRENGTH</b>	6825 psi
<b>100% MODULUS</b>	4700 psi
<b>200% MODULUS</b>	6600 psi
<b>300% MODULUS</b>	NA