

C. L. Hauthaway & Sons Corporation
638 Summer Street Lynn, MA 01905-2092

781 592-6444
www.hauthaway.com

Hauthane L-2969

- DESCRIPTION:** A soft, aliphatic, polyester-based, aqueous polyurethane dispersion.
- SUGGESTED USES:** **L-2969** was designed primarily for use on flexible substrates as a coating, saturant or impregnant. L-2969 may also be used as a blending resin with harder polyurethane dispersions to impart flexibility without adversely effecting chemical resistance.
- CHARACTERISTICS:**
- < Outstanding toughness and abrasion resistance
 - < Excellent water and chemical resistance
 - < Exceptionally high melting point for a medium soft polymer
 - < Can be crosslinked to enhance performance
 - < Dilution and clean-up with water
 - < Contains dipropylene glycol dimethyl ether co-solvent
- APPLICATION:** **L-2969** can be used as a sole vehicle or blended with harder polyurethane dispersions or acrylic emulsions for spray or rotogravure applications. Rheology modifications can be made with associative thickeners for alternative application methods.
- CURING:** The addition of coalescing solvent is recommended to achieve optimal film formation with L-2969. In ambient-cured systems the addition of 5-10% DPnB coalescing solvent is suggested. Less coalescing solvent is required in heat-cured systems to attain comparable film properties. Typical drying temperatures and dwell times for aqueous coatings are sufficient to produce optimal film properties. L-2969 may be crosslinked with carbodiimides, water-dispersible isocyanates or polyaziridines to further enhance performance.

PHYSICAL PROPERTIES

SOLIDS	35% (±1%)
VISCOSITY	75-200 cps
pH	8.5-10.0
DENSITY	8.7 lbs/gal
SOFTENING POINT	325°F
VOC CONTENT	107 g/l (as supplied)
SWARD HARDNESS	10

TENSILE PROPERTIES

(TESTED AT 20 INCHES/MINUTE)	
ELONGATION	500%
TENSILE STRENGTH	>5000 psi
100% MODULUS	700 psi
200% MODULUS	1100 psi
300% MODULUS	2000 psi